



# Centrum stavebního inženýrství a.s.

Fire Technical Laboratory

AUTHORIZED  
BODY No. 212

NOTIFIED  
BODY No. 1390

## CLASSIFICATION OF REACTION TO FIRE IN ACCORDANCE WITH ČSN EN 13501-1+A1:2010

**Applicant:** Příhoda s.r.o.  
Za Radnicí 476  
539 01 Hlinsko  
Czech Republic

**Prepared by:** Centrum stavebního inženýrství a.s.  
Pražská 16  
102 00 Praha 10  
Czech Republic

**Product name:** Textile product „Příhoda PLS“ / Textile  
product „Příhoda NLS“

**Classification  
report No.:** PK-15-024

**Issue number:** 1/2

**Date of issue:** 12<sup>th</sup> March 2015

This classification report consists of 4 pages and may only be used or reproduced in its entirety.

Address:  
PRAŽSKÁ 16, 102 00 PRAHA 10, Czech Republic, E mail: csias@csias.cz, <http://www.csias.cz>  
Reg. No. 45274860, VAT No. CZ45274860. The Company is registered in the Commercial Register  
administered by the Municipal Court of Prague (section B, inset 1595).  
Fire Technical Laboratory, E-mail: ptl@csias.cz  
Phone: +420 281 017 111, Fax: +420 281 017 455

## 1. DETAILS OF CLASSIFIED PRODUCT

### Nature and end use application:

The classification of the product *Textile product „Příhoda PLS“ / Textile product „Příhoda NLS“* is valid for the following end use application:

Hanged textile air distribution system

### Description:

The product *Textile product „Příhoda NLS“* is fully described in the test reports in support of the classification listed in clause 2. The product *„Příhoda NLS“* was selected for reaction to fire tests. Product *„Příhoda PLS“* has the same composition and as the tested *„Příhoda NLS“*. The products differ only in the different air permeability.

## 2. TEST REPORTS AND TEST RESULTS IN SUPPORT OF THIS CLASSIFICATION

### Test reports

Name of laboratory	Name of sponsor	Test report ref. no.	Test method
CSI a.s., Fire technical laboratory	Příhoda s.r.o.	15/461/P211	ČSN EN ISO 11925-2
		15/462/P212	ČSN EN 13823

### Measured values a test results

Test method	Parameter	Number of test	Results	
			Continuous parameter mean (m)	Compliance parameters
ČSN EN ISO 11925-2 exposition = 30 s	$F_s \leq 150 \text{ mm}^{(1)}$ ignition of filter paper <sup>(1)</sup>	6	yes	yes (B to D)
		6	no	no (d0)
	$F_s \leq 150 \text{ mm}^{(2)}$ ignition of filter paper <sup>(2)</sup>	6	yes	yes (B to D)
		6	no	no (d0)
ČSN EN 13823	$FIGRA_{0,2 \text{ MJ}} \text{ (W/s)}$	3	6,6	$\leq 120 \text{ (B)}$
	$LFS < \text{edge}$	3	yes	yes (B)
	$THR_{600 \text{ s}} \text{ (MJ)}$	3	1,1	$\leq 7,5 \text{ (B)}$
	$SMOGR \text{ (m}^2/\text{s}^2)$	3	0	$\leq 30 \text{ (s1)}$
	$TSP_{600 \text{ s}} \text{ (m}^2)$	3	7,8	$\leq 50 \text{ (s1)}$
	flaming droplets / particles	3	no	no (d0)

(1): surface flame attack

(2): edge flame attack

### 3. CLASSIFICATION AND DIRECT FIELD OF APPLICATION

#### Reference and direct field of application

This classification has been carried out in accordance with the clauses 11.6, 11.9.2 and 11.10.1 of ČSN EN 13501-1+A1:2010.

#### Classification

The product *Textile product „Příhoda PLS“ / Textile product „Příhoda NLS“*, in relation to its reaction to fire behaviour is classified:

**B**

The additional classification in relation to smoke production is:

**s1**

The additional classification in relation to flaming droplets/particles is:

**d0**

The format of the reaction to fire classification for *Textile product „Příhoda PLS“ / Textile product „Příhoda NLS“* is:

Fire behaviour		Smoke production			Flaming droplets	
B	-	s	1	,	d	0

**Reaction to fire classification: B-s1, d0**

#### Field of application

This classification is also valid for the following product parameters:

- Mass per unit area  $\leq 80 \text{ g/m}^2$

This classification is valid for the following end use conditions:

- Without substrate

## 4. LIMITATIONS


### Restrictions

This classification report is valid until 12<sup>th</sup> March 2020, provided that the technical specifications of the product will not be changed.

### Warning

This document does not represent type approval or certification of the product.

Prepared:



Jiří Socha



Reviewed:



Vít Slaboch  
technical manager of laboratory